

**DESCRIPTION:**

Western Colloid **WCP-SF** (Western Colloid W-26 Firm or Tietex T326) is a 2.75 ounce stitchbonded style polyester fabric with a firm finish used in the reinforcement of cold process roofing systems. It is also used as a flashing reinforcement with mastics and elastomerics. **WCP-SF** has good strength and elongation making it an excellent reinforcement for water base cold process and maintenance roof systems.

**WCP-SF** has a firm but pliable finish. It will provide good conformability on smooth or semi-smooth surfaces. **WCP-SF** works well when used over smooth or cap sheet surfaces. It has fewer stitches per inch, which allows for better wetability, which requires less brooming. Because it has a firm (starched) finish it will have fewer wrinkles and will lay straighter and smoother during application.

**WCP-SF** is available in: 10 square rolls (40" x 324')

**PROPERTIES:**

Weight		2.75 ounce sq. yd.
Thickness		.25 in.
Tensile avg.	ASTM D 1682	41. lbs.**
Elongation	ASTM D 1682	25%**
Burst Strength	ASTM D 3786	127. lbs.
Trapezoid Tear Strength	ASTM D 1117	14. lbs.**

\*\*Average machine and cross machine direction.