

FLUID APPLIED REINFORCED ROOFING

Application Steps**

Region 1 - Western U.S.
Region 2 - Hawaii/Pacific

File No.	Specification No.	Step1	Step 2	Step 3	Step4	Step 5	Step 6	Step 7	Step 8
6	SM-1P-10-A	5 gal. Emulsion	1 Poly	5 gal. Emulsion	1½ gal. SilverWhite	----	----	----	----
7	SM-1P-XE	6 gal. Emulsion	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	----	----	----	----
8	SM-2P-16-A	6 gal. Emulsion	1 Poly	5 gal. Emulsion	1 Poly	5 gal. Emulsion	1½ gal. SilverWhite	----	----
9	SM-2P-XE	6 gal. Emulsion	1 Poly	6 gal. Emulsion	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	----	----
10	GR-2P-24-XE	Flood Emulsion**	6 gal. Emulsion	1 Poly	6 gal. Emul.	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	----
15a	SMAA-1P-6xE	3 gal. ElastaHyde	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	----	----	----	----
15b	SMAA-1P-7xE	3 gal. ElastaHyde	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	1 gal. ElastaHyde	----	----	----
15c	SMAA-2P-8xE	3 gal. ElastaHyde	1 Poly	2 gal. ElastaHyde	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	----	----
18	SMEA-2P-6xE	6 gal. Emulsion	1 Poly	3 gal. ElastaHyde	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde	----	----
19	SMEA-3P-6xE	6 gal. Emulsion	1 Poly	6 gal. Emulsion	1 Poly	3 gal. ElastaHyde	1 Poly	1½ gal. ElastaHyde	1½ gal. ElastaHyde

** Chart references standard application rates for referenced specifications. Rates may vary on a per project basis. ElastaHyde product number may vary by region and existing conditions. Consult Western Colloid for additional specifications, application rates and product requirements.